Technical Data Sheet

GB 730 - Wood Interior

March 2026

Product Description

GB 730 Wood Interior provides the following product characteristics:

Technology	Synthetic resin dispersion
Application	Wood working Industry

Application

- Wood working

GB 730 Wood Interior is a medium setting woodworking adhesive designed for:

- General purpose wood working applications
- Hot and cold pressing paper foil to Chipboard

Technical Data

Viscosity	± 12000 mPa.s Brookfield @ 25°C
Solids	± 43%
Appearance	Off White liquid

Application Method

Stir well before use. GB 730 Wood Interior has a medium viscosity and excellent flow properties. The adhesive can be applied with most conventional methods i.e. brush, hand roller and mechanical rollers.

GB 730 Wood Interior demonstrates the following properties

- Medium drying set speed thus allowing sufficient open time (± 20 minutes) for woodworking applications where by an open time is required
- Easy cleaning with cold water
- Good machine ability
- Tough impact resistance glue line
- Good gap fill properties

Cleaning

Whilst GB 730 Wood Interior still wet, application systems can be cleaned with water. Dried residue can be removed with the GB Water base Cleaner which is available for industrial and HACCP requirements. Contact our technical team to advise which grade would be suitable.

Storage Conditions

GB 730 Wood Interior should be stored under cover at temperatures between 20°C to 30°C. Container lids must be tightly closed when the product is not in use. Stocks should be rotated to avoid the use of overaged products.

Shelf Life

Under the above storage conditions GB 730 Wood Interior has a maximum shelf life of 6 months.

Additional Information

Disclaimer:
The information provided herein, specifically the recommendations for usage and application of our products, is based upon our knowledge and experience. Due to the different materials used as well as the variable working environment beyond our control, we request that intensive trials are done to test the suitability of our products with regards to the required processes and applications. We do not accept any liability with regards to any verbal recommendation, except for the cases where we are liable of gross negligence or false intention. This data sheet replaces all former versions.

Application Properties

Email: swachemgm@swacogroup.com
Address: 2 - 8 Walter Street, Southern Industrial Area, Windhoek
Tel: +264 (0)61 235 051